

**PLASTUB® PVC33**

**PVC tube 70 Shore A  
Opaque**



**Description**

Polyvinyl chloride extruded tube

**Applications**

Unpressurised transport of fluids  
Disposable media

**Fields**

Miscellaneous industries, irrigation etc.

**General characteristics**

- Economic, good weather resistance
- Recyclable

**Technical data**

- Temperature of use: -30 to +50°C
- Nominal hardness: **70 Shore A**  
as per ISO R 868
- Nominal density: 1.46 as per ISO 1183
  - Tensile strength: >11 Mpa  
as per ISO R 527
  - Elongation at break: >250 %  
as per ISO R 527
  - Standard colour: opaque
- Recommended connection: nipple with lug clamp or band clamp

**Options (contact us)**

- Other diameters
- Other solid colours
  - Cut to lengths
- Other packaging
  - Surface marking
- Additives: Anti-UV, antibacterial etc.
  - Pre-cut rolls

Nominal internal diameter (mm)	Nominal outside diameter (mm)	Nominal thickness (mm)	Nominal linear weight (g/m)	Standard packaging Roll (m)
2	4	1	14	250
2	6	2	37	250
3	5	1	19	250
3	6	1,5	31	200
4	6	1	23	250
4	7	1,5	38	100
4	8	2	55	100
4	9	2,5	75	100
5	7	1	28	100
5	8	1,5	45	100
5	9	2	65	100
5	10	2,5	86	100
5	15	5	230	25
6	8	1	32	100
6	9	1,5	52	100
6	10	2	74	100
6	12	3	124	50
6	18	6	330	25
7	10	1,5	59	100
8	11	1,5	66	100
8	12	2	92	100
8	14	3	151	50
8	16	4	220	25
8	20	6	385	25
9	12	1,5	73	50
9	13	2	101	50
9	14	2,5	132	50
9	18	4,5	277	25
10	13	1,5	80	50
10	14	2	110	50
10	17	3,5	217	25
10	18	4	257	25
10	20	5	344	25
10	25	7,5	602	25
11	15	2	119	50
12	16	2	128	50
12	17	2,5	166	50
12	21	4,5	341	25
13	23	5	413	25
14	18	2	147	25
14	23	4,5	382	25
15	20	2,5	201	25
15	21	3	248	25
16	20	2	165	25
16	26	5	483	25
18	24	3	289	25
20	25	2,5	258	25
20	26	3	317	25
21	26	2,5	270	25
22	29	3,5	410	25
27	34	3,5	490	25
36	43	3,5	634	25
40	48	4	807	25
47	55	4	936	25

Standard tolerances: refer to pages 115 to 118.

**Variant**

PLASTUB® PVC 32  
PVC tube 76 Shore A  
Opaque



Zone Industrielle 63600 AMBERT - France  
Tel. + 33 (0)4 73 82 44 36  
e-mail: [plastub@omerin.com](mailto:plastub@omerin.com)

[www.plastub.fr](http://www.plastub.fr)

The information given in this technical data sheet is indicative and subject to change without prior notice. As the conditions of use and the environment in which the product is used cannot be fully covered in our design work, PLASTUB shall not assume liability for any incidents in the event of inappropriate use and/or not carried out according to best practices and applicable standards.

To ensure optimal use of our products, we recommend full tests in real-life situations.

To this end, our sales department is on hand to supply samples and/or to examine the conditions of comprehensive testing in our laboratories.

© Registered trademark of PLASTUB. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of PLASTUB.