

## PLASTUB® PVC42

### PVC/NBR tube 74 Shore A Black



#### Description

Polyvinyl chloride and nitrile rubber extruded tube

#### Applications

Unpressurised transport of air, fluids

#### Fields

Unpressurised transfer and backflow of certain hydrocarbons

#### General characteristics

- Good weather resistance, improved resistance to hydrocarbons
- Recyclable

#### Technical data

- Temperature of use: -30 to +50°C
- Nominal hardness: **74 Shore A** as per ISO R 868
- Nominal density: 1.29 as per ISO 1183
  - Tensile strength: >15 Mpa as per ISO R 527
  - Elongation at break: >320 % as per ISO R 527
  - Standard colour: black
- Recommended connection: nipple with lug clamp or band clamp

#### Options (contact us)

- Other diameters
- Cut to lengths
- Other packaging
- Surface marking
- Additives: Anti-UV, antibacterial etc.
- Pre-cut rolls

Nominal internal diameter (mm)	Nominal outside diameter (mm)	Nominal thickness (mm)	Nominal linear weight (g/m)	Standard packaging Roll (m)
2	4	1	12	250
2	6	2	32	250
3	5	1	16	250
3	6	1,5	27	200
4	6	1	20	250
4	7	1,5	33	100
4	8	2	49	100
4	9	2,5	66	100
5	7	1	24	100
5	8	1,5	39	100
5	9	2	57	100
5	10	2,5	76	100
5	15	5	203	25
6	8	1	28	100
6	9	1,5	46	100
6	10	2	65	100
6	12	3	109	50
6	18	6	292	25
7	10	1,5	52	100
7	12	2,5	96	50
7	14	3,5	149	50
8	10	1	36	100
8	11	1,5	58	100
8	12	2	81	100
8	14	3	134	50
8	16	4	194	25
8	20	6	340	25
9	12	1,5	64	50
9	13	2	89	50
9	14	2,5	116	50
9	18	4,5	246	25
10	13	1,5	70	50
10	14	2	97	50
10	17	3,5	191	25
10	18	4	227	25
10	20	5	304	25
10	25	7,5	532	25
11	15	2	105	50
12	16	2	113	50
12	17	2,5	147	50
12	21	4,5	301	25
13	23	5	365	25
14	18	2	130	25
14	23	4,5	337	25
15	20	2,5	177	25
15	21	3	219	25
16	20	2	146	25
16	26	5	425	25
18	24	3	255	25
20	25	2,5	228	25
20	26	3	279	25
21	26	2,5	238	25
22	29	3,5	362	25
27	34	3,5	432	25
36	43	3,5	560	25
40	48	4	713	25
47	55	4	826	25

Standard tolerances: refer to pages 115 to 118.



Zone Industrielle 63600 AMBERT - France  
Tel. + 33 (0)4 73 82 44 36  
e-mail: [plastub@omerin.com](mailto:plastub@omerin.com)

[www.plastub.fr](http://www.plastub.fr)

The information given in this technical data sheet is indicative and subject to change without prior notice. As the conditions of use and the environment in which the product is used cannot be fully covered in our design work, PLASTUB shall not assume liability for any incidents in the event of inappropriate use and/or not carried out according to best practices and applicable standards.

To ensure optimal use of our products, we recommend full tests in real-life situations.

To this end, our sales department is on hand to supply samples and/or to examine the conditions of comprehensive testing in our laboratories.

© Registered trademark of PLASTUB. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of PLASTUB.