THERMOPLASTIC OR SPECIAL POLYMER **EXTRUDED TUBES WITH REINFORCING** SHEATH

TUBOL® PTFEP

PTFE tube with PVC sheath



Description

Polytetrafluoroethylene extruded tube, polyvinyl chloride sheath

Applications

Pressurised transport of chemically aggressive fluids, gas

Fields

Medical, pharmaceutical, agriculture, laboratory, cosmetics

General characteristics

 Sparkproof sheath • Good resistance to impacts and abrasion Very good UV resistance • Excellent chemical resistance

Technical data

• Standard: * Tube material FDA-approved 21 CFR 177 1550

• Temperature of use: -20 to +90°C

• Tube: ELASTUB® PTFE translucent

• Sheath: PLASTUB® GR black -Non flame-propagating PVC type C2

as per NF C 32070

• Recommended connection:

compression tube fittings

Options (contact us)

- Other diameters
- Other packaging
- Surface marking
- Other tube and/or sheath colours • Other qualities of interior tubes
- Other qualities of external sheaths

| Nominal internal diameter | Nominal outside diameter | External diameter on sheath | Bending radius* | Operating pressure* | Burst pressure* | Nominal linear weight |
|---------------------------------|--------------------------------|-----------------------------------|--------------------|---------------------|--------------------|-----------------------------|
| (mm) | (mm) | (mm) | (mm) | (bar) | (bar) | (g/m) |
| 4 | 6 | 8 | 40 | 15 | 60 | 66 |
| 6 | 8 | 10 | 60 | 11 | 44 | 89 |
| 8 | 10 | 12 | 80 | 9 | 36 | 111 |
| 10 | 12 | 14 | 100 | 8 | 32 | 184 |

| Nominal internal diameter | Standard packaging Roll Drum | | | |
|---------------------------------|------------------------------|--------|--|--|
| diameter | Kott | Didili | | |
| (mm) | (m) | (m) | | |
| | | | | |
| 4 | 100 | 500 | | |
| 6 | 100 | 500 | | |
| 8 | 100 | - | | |
| 10 | 100 | - | | |

Standard tolerances: refer to pages 115 to 118.
*Values provided for information purposes for an ambient temperature of 23°C.



The information given in this technical data sheet is indicative and subject to change without prior notice. As the conditions of use and the environment in which the product is used cannot be fully covered in our design work, PLASTUB shall not assume liability for any incidents in the event of inappropriate use and/or not carried out according to best practices and applicable standards.

To ensure optimal use of our products, we recommend full tests in real-life situations.

To this end, our sales department is on hand to supply samples and/or to examine the conditions of comprehensive testing in our laboratories.

® Registered trademark of PLASTUB. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of PLASTUB.

Zone Industrielle 63600 AMBERT - France Tel. + 33 (0)4 73 82 44 36 e-mail: plastub@omerin.com

www.plastub.fr