



QUAL'IFT® ETV

EPDM hose with polyester / glass fibre braid DN10 to 20



► **Composition:**

- EPDM tube according to EN 681-1 type WB
- Polyester / fibreglass braid

► **Lengths:**

See table below

Roll packaging

(other types of packaging on request)

► **Application:**

- Water passage for sanitary, heating and air conditioning (max glycol content : 40%)
- Aqueous solutions

► **Technical data**



Operating temperature
-15°C to +90°C peaks at +110°C



Max operating pressure
16 Bar (DN10)
10 Bar (DN15)
6 Bar (DN20)



See table below



KEY BENEFITS

- Excellent corrosion and ageing resistance
- **Withstands accidental heating**
- Absorbs expansion and water hammer
- Accidental abrasion resistance
- Good UV resistance
- Does not transmit hose noise



ASSEMBLY

► **QUAL'IFT®** hoses must be assembled by scrupulously following the recommended rules and stages in paragraph "Recommendations for use"



CUSTOM OFFER

- Contact us for all your specific requirements

► **Hoses for your low-pressure applications /** References & Compositions

| Reference | DN (mm) | Diameter int. x ext. (mm) | Burst pressure (Bar) | MOQ (m) | Bending radius (mm) |
|-----------|---------|---------------------------|----------------------|------------|---------------------|
| ETV 10 | 10 | 9.5 x 14 | 110 | Contact us | 60 |
| ETV 15 | 15 | 15 x 22 | 80 | | 88 |
| ETV 20 | 20 | 20 x 28 | 60 | | 112 |



IFT Groupe Omerin SAS
Zone Industrielle - F 63600 Ambert
Tel: +33 (0)4 73 82 32 33
ift@omerin.com

www.flexibles.com

The information provided on this data sheet is indicative and subject to change without notice. All hoses ordered must comply with IFT's installation recommendations, which can be viewed in its catalogue. IFT can under no circumstances be held liable for any incidents arising from inappropriate use, particularly in the case of installation not carried out in accordance with the rules of the trade and the standards in force. © Registered trademark of IFT. Drawings and photos are not contractually binding. Reproduction is prohibited without the prior consent of IFT.