

HIGH TEMPERATURE WIRES AND CABLES
FOR THE GENERAL MARKET
SECTION I: CROSS LINKED ELASTOMERS

SILICONE INSULATED AND/OR SHEATHED
WIRES AND CABLES

SILICABLE® CS-ES and ECS-ES

Extra-flexible core
-60 °C to +180 °C



- 1 • Extra-flexible bare copper (ref. CS-ES) or tin-plated (ref. ECS-ES) core - class 6 as per IEC 60228.
- 2 • Insulation: Silicone rubber.

Approvals - standards

- Halogen-free: IEC 60754-1 / EN 60754-1.
- Low corrosivity of gas emissions: IEC 60754-2 / EN 60754-2.
 - Low smoke density: IEC 61034-2 / EN 61034-2.
 - Fire retardant: NF C 32-070 test C1.

Applications

- Cabling for alternate bending use, cabling requiring a low bending radius.
- Cabling for household electrical heating appliances or industrial appliances requiring the use of highly flexible cables.
- Measuring cables.

Options

- Outer electrical shielding:
 - > Tin-plated copper braid: ref. CSBE-ES or ECSBE-ES.
 - Outer Flexible armour:
 - > Galvanised steel braid: ref. CSBG-ES or ECSBG-ES.
 - > Stainless steel braid: ref. CSBI-ES or ECSBI-ES.
- Other nominal cross-sections: contact us.
- Other nominal stranding: contact us.
- Other options: contact us.

Characteristics

General

- Continuous operating temperatures: -60 °C to +180 °C.
- Good resistance to thermal shock and UV.
- Excellent alternate bending strength.

Electrical

- | | | |
|------------------|----------------------------------|-------------------------------|
| | S < 2.5 mm² | S ≥ 2.5 mm² |
| • Rated voltage: | 300/500 V | 600/1000 V. |
| • Test voltage: | 2000 V | 3000 V. |

Standard products

- Up to 120 mm²: all colours including two-coloured.
- From 150 mm² to 240 mm²: all colours except two-coloured.

CS-ES and ECS-ES

Extra-flexible core • class 6 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Max. linear resistance at 20 °C (Ω/km) (bare copper core)
0.5	260 x 0.05 or 130 x 0.07	39.0
0.75	390 x 0.05 or 200 x 0.07	26.0
1	520 x 0.05 or 260 x 0.07	19.5
1.5	390 x 0.07 or 190 x 0.10	13.3
2.5	650 x 0.07 or 320 x 0.10	7.98
4	1008 x 0.07 or 224 x 0.15	4.95
6	342 x 0.15 or 192 x 0.20	3.30
10	324 x 0.20	1.91
16	512 x 0.20	1.21
25	796 x 0.20	0.780
35	1120 x 0.20	0.554
50	1600 x 0.20	0.386
70	2240 x 0.20	0.272
95	3025 x 0.20	0.206
120	3820 x 0.20	0.161
150	4775 x 0.20	0.129
185	5888 x 0.20	0.106
240	7639 x 0.20	0.0801

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.6	2.1	8.6
0.6	2.4	11.8
0.6	2.5	14.0
0.6	2.8	19.1
0.7	3.4	30.3
0.8	4.2	47.0
0.8	5.0	69.7
1.0	6.4	115
1.2	7.8	180
1.4	9.6	275
1.4	11.0	377
1.6	13.2	546
1.6	14.8	731
1.8	17.4	980
1.8	19.4	1312
2.0	21.4	1562
2.2	23.9	1899
2.2	26.4	2496

For this product, please contact:

OMERIN division principale

Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

OMERIN division silisol

BP 87 - ZI du Devey - F 42000 Saint-Etienne
Tel. +33 (0)4 77 81 36 00 - Fax +33 (0)4 77 81 37 00
silisol@omerin.com

www.omerin.com

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.
© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.