

PLASTHERM® PHF2

Halogen-free insulation flame retardant

-40 °C to +105 °C

Approvals - standards

- Resistance to vertical flame propagation for a single insulated wire. IEC 60332-1-2 / NF C 32-070 test C2
- Tests on electric cables under fire conditions as per IEC 60332-3-22 (category A): ISSEP test reports no. 1524/2015
- Classification C1 as per NF C 32-070 test no. 1 (LCIE report no. 12/108571-616378A)
- Halogen-free, low corrosivity and acidity of gases evolved during combustion: EN 60754-1 and EN 60754-2
- Low smoke opacity: EN 61034-2

Applications

- Internal cabling for electrical and electronic appliances

Characteristics

General

- Continuous operating temperatures: -40 °C to +105 °C.
- Halogen-free, flame retardant, low toxicity, corrosivity and smoke opacity
- Good flexibility and mechanical strength, excellent resistance to abrasion.

Electrical


- Rated voltage: 600/1 000 V.
- Test voltage: 3 000 V.

Standard products

- All solid colours + two-coloured yellow/green

Options

- Solid bare copper core, class 1 as per IEC 60228: ref. PHF2R, see table below).
- American cross-sections AWG: Contact us



- 1 • Flexible bare copper (PHF2) or tin-plated (PHF2E) core – Class 5 as per IEC 60228.
- 2 • Halogen-free, flame-retardant thermoplastic insulation.

PLASTHERM PHF2 and PHF2E

Flexible core • class 5 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)	
		PHF2	PHF2E
0.5	16 x 0.20	39.0	40.1
0.75	24 x 0.20	26.0	26.7
1	32 x 0.20	19.5	20.0
1.5	30 x 0.25	13.3	13.7
2.5	50 x 0.25	7.98	8.21
4	56 x 0.30	4.95	5.09
6	84 x 0.30	3.30	3.39
10	80 x 0.40	1.91	1.95
16	126 x 0.40	1.21	1.24
25	196 x 0.40	0.78	0.795
35	276 x 0.40	0.554	0.565
50	396 x 0.40	0.386	0.393
70	360 x 0.50	0.272	0.277
95	485 x 0.50	0.206	0.210
120	608 x 0.50	0.161	0.164
150	756 x 0.50	0.129	0.132
185	944 x 0.50	0.106	0.108
240	1221 x 0.50	0.0801	0.0817
300	1525 x 0.50	0.0641	0.0654

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.6	2.20	9.1
0.6	2.40	11.9
0.7	2.70	15.2
0.8	3.10	22.3
0.8	3.60	33.4
0.9	4.30	50.1
0.9	5.00	72.5
0.9	6.10	113
1.0	7.10	170
1.0	8.70	256
1.1	10.3	364
1.1	12.1	510
1.1	13.9	692
1.4	16.6	972
1.4	18.2	1202
1.6	20.2	1503
1.6	22.4	1849
1.8	25.4	2376
1.8	27.6	2909

Option: PLASTHERM PHF2R

Solid core • class 1 as per IEC 60228

Nominal cross-section (mm ²)	Nominal stranding	Maximum linear resistance at 20 °C (Ω/km)
0.5	1 x 0.80	36.0
0.75	1 x 0.98	24.5
1	1 x 1.13	18.1
1.5	1 x 1.38	12.1
2.5	1 x 1.77	7.41
4	1 x 2.24	4.61

INSULATED WIRE OR CABLE

Nominal thickness of insulation (mm)	Nominal diameter (mm)	Approximate linear weight (kg/km)
0.6	2.00	9.35
0.6	2.20	12.2
0.7	2.60	15.1
0.7	2.80	21.6
0.8	3.40	32.1
0.8	4.00	48.7

For this product, please contact:

OMERIN division principale
Zone Industrielle - F 63600 Ambert
Tel. (33) 04 73 82 50 00 - Fax (33) 04 73 82 50 10
omerin@omerin.com

www.omerin.com

omerin
LES CABLES DE L'EXTREME

The information provided in this technical data sheet is indicative and may be modified without prior notice, laying, wiring and electrical conditions and the environment of the cable can not be fully considered in our studies. In no way the company OMERIN shall be held responsible for any incidents in the case of inappropriate uses, particularly in the case of wiring conditions that do not respect the good practice and the standards in force. For an optimum use of the cables produced by our company, we recommend testing in real conditions. Our sales department is available for a possible provision of samples, and/or for the conditions of a complete study in our laboratories.

© Registered trademark of the OMERIN Group. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of OMERIN.