THERMOPLASTIC EXTRUDED RODS & CORDS

RODS, CORDS & PROFILES

PLASCORD® PVC33

PVC rod 70 Shore A Crystal



Description

Polyvinyl chloride extruded rod

Applications

Production of bolt ropes, leaktight seals

Fields

Tarpaulin, sail, canvas, blind manufacturers

General characteristics

- Very flexible
- Economical
- Recyclable

Technical data

• Temperature of use: -30°C to +70°C

• Nominal hardness: **70 Shore A**

as per ISO R 868

• Nominal density: 1.46 as per ISO 1183

• Tensile strength: >11 Mpa as per ISO R 527

• Elongation at break: >250 %

as per ISO R 527

• Standard colour: black

Options (contact us)

Other diameters

• Other solid colours

Cut to lengths

Other packaging

• Surface marking • Additives: Anti-UV, antibacterial etc.

Nominal outside diameter (mm)	Nominal linear weight (g/m)	Standard packaging Roll (m)
1	1	500
2	4	500
3	10	250
4	18	250
5	28	250
6	41	250
8	73	100
10	114	100
12	165	100
14	225	100
15	258	100
20	459	50
25	717	25
30	1,032	25
35	1,404	25
40	1,835	25

Standard tolerances: refer to pages 115 to 118.

Variant

PLASCORD® PVC32 PVC rod 76 Shore A black



The information given in this technical data sheet is indicative and subject to change without prior notice. As the conditions of use and the environment in which the product is used cannot be fully covered in our design work, PLASTUB shall not assume liability for any incidents in the event of inappropriate use and/or not carried out according to best practices and applicable standards.

To ensure optimal use of our products, we recommend full tests in real-life situations.

To this end, our sales department is on hand to supply samples and/or to examine the conditions of comprehensive testing in our laboratories.

® Registered trademark of PLASTUB. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of PLASTUB.

Zone Industrielle 63600 AMBERT - France Tel. + 33 (0)4 73 82 44 36 e-mail: plastub@omerin.com

www.plastub.fr