

THERMOPLASTIC EXTRUDED SLEEVINGS

SLEEVINGS

PLASTUB® GS

PVC sleeving 84 Shore A
70°C, crystal



Description

Polyvinyl chloride extruded sleeving

Applications

Mechanical and electrical protection for cable harnesses

Fields

Industrial cabling, miscellaneous industries

General characteristics

- Very flexible
- Economical
- Recyclable

Technical data

- Standard: NF EN 60684-2
- Temperature of use: **-20°C to +70°C**
 - Dielectric rigidity: 16 Kv/mm
 - Nominal hardness: 84 Shore A as per ISO R 868
- Nominal density: 1.24 as per ISO 1183
 - Tensile strength: >21 Mpa as per ISO R 527
- Elongation at break: >320 % as per ISO R 527
 - Standard colour: crystal

Options (contact us)

- Other diameters
- Other solid colours
 - Cut to lengths
- Other packaging
 - Surface marking
- Additives: Anti-UV, antibacterial etc.
 - Pre-split versions

Nominal internal diameter (mm)	Nominal outside diameter (mm)	Nominal thickness (mm)	Nominal linear weight (g/m)	Standard packaging Roll (m)
0,5	1,2	0,35	1	500
1	1,8	0,4	2	500
1,5	2,3	0,4	3	500
2	2,8	0,4	4	500
2	3	0,5	5	500
2,5	3,3	0,4	5	500
3	3,8	0,4	5	500
3	4	0,5	7	500
3,5	4,3	0,4	6	500
4	4,8	0,4	7	500
4	5	0,5	9	500
5	5,8	0,4	8	500
5	6	0,5	11	500
6	6,9	0,45	11	400
7	8	0,5	15	250
8	9	0,5	17	250
9	10	0,5	18	200
10	11	0,5	20	150
11	12	0,5	22	100
13	14,2	0,6	32	100
14	15,2	0,6	34	50
15	16,2	0,6	36	50
16	17,3	0,65	42	50
18	19,5	0,75	55	50
20	22	1	82	50
22	24	1	90	50
24	26	1	97	50
25	27	1	101	50
26	28	1	105	25
28	30	1	113	25
30	32	1	121	25

Standard tolerances: refer to pages 115 to 118.



Zone Industrielle 63600 AMBERT - France

Tel. + 33 (0)4 73 82 44 36

e-mail: plastub@omerin.com

www.plastub.fr

The information given in this technical data sheet is indicative and subject to change without prior notice. As the conditions of use and the environment in which the product is used cannot be fully covered in our design work, PLASTUB shall not assume liability for any incidents in the event of inappropriate use and/or not carried out according to best practices and applicable standards.

To ensure optimal use of our products, we recommend full tests in real-life situations.

To this end, our sales department is on hand to supply samples and/or to examine the conditions of comprehensive testing in our laboratories.

© Registered trademark of PLASTUB. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of PLASTUB.