

THERMOPLASTIC EXTRUDED SLEEVINGS

SLEEVINGS

PLASTUB® GTHT PVC sleeving 85 Shore A 125°C, black



Description

Polyvinyl chloride extruded sleeving

Applications

Mechanical and electrical protection for cable harnesses

Fields

Automobile, industrial cabling

General characteristics

- Recyclable
- Improved resistance to temperature
- Technical data**
 - Standard: NF EN 60684-2
 - Temperature of use: **-40°C to +125°C**
 - Dielectric rigidity: 16 Kv/mm
 - Nominal hardness: 85 Shore A as per ISO R 868
- Nominal density: 1.22 as per ISO 1183
 - Tensile strength: >18 Mpa as per ISO R 527
- Elongation at break: >320 % as per ISO R 527
 - Standard colour: black

Options (contact us)

- Other diameters
- Other solid colours
 - Cut to lengths
- Other packaging
- Surface marking
- Pre-split versions

Nominal internal diameter (mm)	Nominal outside diameter (mm)	Nominal thickness (mm)	Nominal linear weight (g/m)	Standard packaging Roll (m)
0,5	1,2	0,35	1	500
1	1,8	0,4	2	500
1,5	2,3	0,4	3	500
2	2,8	0,4	4	500
2	3	0,5	5	500
2,5	3,3	0,4	4	500
3	3,8	0,4	5	500
3	4	0,5	7	500
3,5	4,3	0,4	6	500
4	4,9	0,45	8	500
4	5	0,5	9	500
5	5,8	0,4	8	500
5	6	0,5	11	500
6	6,9	0,45	11	400
7	8	0,5	14	250
8	9	0,5	16	250
9	10	0,5	18	200
10	11	0,5	20	150
11	12	0,5	22	100
12	13,1	0,55	26	100
13	14,2	0,6	31	100
14	15,2	0,6	34	50
15	16,2	0,6	36	50
16	17,3	0,65	41	50
18	19,5	0,75	54	50
20	22	1	80	50
22	24	1	88	50
24	26	1	96	50
25	27	1	100	50
26	28	1	103	25
28	30	1	111	25
30	32	1	119	25

Standard tolerances: refer to pages 115 to 118.



Zone Industrielle 63600 AMBERT - France
Tel. + 33 (0)4 73 82 44 36
e-mail: plastub@omerin.com

www.plastub.fr

The information given in this technical data sheet is indicative and subject to change without prior notice. As the conditions of use and the environment in which the product is used cannot be fully covered in our design work, PLASTUB shall not assume liability for any incidents in the event of inappropriate use and/or not carried out according to best practices and applicable standards.

To ensure optimal use of our products, we recommend full tests in real-life situations.

To this end, our sales department is on hand to supply samples and/or to examine the conditions of comprehensive testing in our laboratories.

© Registered trademark of PLASTUB. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of PLASTUB.