

**PLASTUB® PVC29**

**PVC tube 68 Shore A  
Food grade crystal**



**Description**

Polyvinyl chloride extruded tube

**Applications**

Unpressurised transport of air, fluids

**Fields**

Various industries, agriculture, laboratories, aquariums etc.

**General characteristics**

- Flexible, economic, versatile
- Wide range of colours
- Good resistance to acids, bases and detergents
- Recyclable

**Technical data**

- Standard: Material suitable for food contact under certain conditions
- Temperature of use: -30 to +50°C
- Nominal hardness: **68 Shore A** as per ISO R 868
- Nominal density: 1.20 as per ISO 1183
  - Tensile strength: >17 Mpa as per ISO R 527
  - Elongation at break: >280 % as per ISO R 527
  - Standard colour: crystal
  - Recommended connection: nipple with lug clamp or band clamp

**Options (contact us)**

- Other diameters
- Other solid colours
  - Cut to lengths
- Other packaging
- Surface marking
- Additives: Anti-UV, antibacterial etc.
  - Pre-cut rolls

Nominal internal diameter (mm)	Nominal outside diameter (mm)	Nominal thickness (mm)	Nominal linear weight (g/m)	Standard packaging Roll (m)
2	4	1	11	250
2	6	2	30	250
3	5	1	15	250
3	6	1,5	25	200
4	6	1	19	250
4	7	1,5	31	100
4	8	2	45	100
4	9	2,5	61	100
5	7	1	23	100
5	8	1,5	37	100
5	9	2	53	100
5	10	2,5	71	100
5	15	5	188	25
6	8	1	26	100
6	9	1,5	42	100
6	10	2	60	100
6	12	3	102	50
6	18	6	271	25
7	10	1,5	48	100
7	12	2,5	89	50
7	14	3,5	138	50
8	10	1	34	100
8	11	1,5	54	100
8	12	2	75	100
8	14	3	124	50
8	16	4	181	25
8	20	6	317	25
9	12	1,5	59	50
9	13	2	89	50
9	14	2,5	108	50
9	18	4,5	229	25
10	13	1,5	65	50
10	14	2	90	50
10	17	3,5	178	25
10	18	4	211	25
10	20	5	283	25
10	25	7,5	495	25
11	15	2	98	50
12	16	2	106	50
12	17	2,5	137	50
12	21	4,5	280	25
13	23	5	339	25
14	18	2	121	25
14	23	4,5	314	25
15	20	2,5	165	25
15	21	3	203	25
16	20	2	136	25
16	26	5	396	25
18	24	3	237	25
20	25	2,5	212	25
20	26	3	260	25
21	26	2,5	221	25
22	29	3,5	336	25
27	34	3,5	402	25
36	43	3,5	521	25
40	48	4	663	25
47	55	4	769	25

Standard tolerances: refer to pages 115 to 118.



Zone Industrielle 63600 AMBERT - France

Tel. + 33 (0)4 73 82 44 36

e-mail: [plastub@omerin.com](mailto:plastub@omerin.com)

[www.plastub.fr](http://www.plastub.fr)

The information given in this technical data sheet is indicative and subject to change without prior notice. As the conditions of use and the environment in which the product is used cannot be fully covered in our design work, PLASTUB shall not assume liability for any incidents in the event of inappropriate use and/or not carried out according to best practices and applicable standards.

To ensure optimal use of our products, we recommend full tests in real-life situations.

To this end, our sales department is on hand to supply samples and/or to examine the conditions of comprehensive testing in our laboratories.

© Registered trademark of PLASTUB. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of PLASTUB.